

Monday August 8<sup>th</sup>, 2023

To Whom It May Concern:

Aztec Tents is a manufacturer of tents and canopies primarily sold to event rental companies throughout the State of California, North America, Europe, and Australia. From as early as the mid 1990's through July of 2020, Aztec Tents was supplied with flame retardant fabrics from California Combining Corporation, of Los Angeles, CA to build the tents it sold to customers across the globe. These fabrics were not treated fabrics, but rather constructed to be inherently flame retardant and compliant with the California Code of Regulations Title 19 Section 1237.1, the requirements of the California Office of the State Fire Marshal (OSFM). These fabrics, at the time were registered with the OSFM under registration number 419.01.

In mid to late 2020, California Combining Corporation ceased operations and dissolved leaving any ability to continue ongoing registration with the State Fire Marshals Office impossible. In response, Aztec Tents through guidance of the OSFM, pursued testing with a State of California approved testing lab Diversified Testing Laboratories Inc. This testing report attached (REF: Diversified\_LAM-TEX\_CATitle19\_1237.1\_121322.pdf) was done on behalf of Aztec Tents and its many customers, including:

Made In the Shade Tent Rentals, (3930 Seaport Blvd Suite A, West Sacramento, CA 95691)

to show that the fabric identified as LAM TEX under previous registration number 419.01 meets California Administrative Code Title 19- Public Safety, Section 1237.1 for Flame Resistance.

In as much as Aztec Tents is only one of several manufacturers that were affected by the dissolution of California Combining Corporation, we are unable to formally register this fabric with the OSFM under the same registration number as previously held by California Combining Corporation for liability reasons. However, we certify that all fabric manufactured by Aztec Tents and labeled using the 419.01 Registration Number were constructed of the same LAM-TEX fabric tested and shown to pass in the attached results.

Aztec Tents expressly grants the usage of these results in conjunction with this letter to Made in the Shade Tent Rentals.

If you have any questions, please reach out to me directly at (310) 347-3010, extension 101.

Sincerely Yours,



Alex Kouzmanoff  
President, Aztec Tents



**DIVERSIFIED**  
TESTING LABORATORIES, INC.  
WORLDWIDE SERVICE

“We Test Per Your Request”

336 WEST FRONT STREET  
P.O. BOX 4004  
BURLINGTON, NORTH CAROLINA 27215  
PHONE (336) 227-7710 • FAX (336) 227-1175  
www.diversifiedtestinglabs.com

December 13, 2022

Mr. Alex Kouzmanoff  
AZTEC TENTS  
2665 Columbia Street  
Torrance, CA 90503

Reference: Laboratory Test Report  
Lab Identification No. 52907  
Invoice No. 84298

Dear Mr. Kouzmanoff:

One (1) fabric sample, identified as **LAM TEX**, was received and tested in accordance with the California Administrative Code Title 19--Public Safety, Section 1237.1 Flame Resistance, Small Scale Test. The results are as follows:

**Test Results**

Specimen Number	After Flame (sec)		Char Length (in)	
	<u>Length</u>	<u>Width</u>	<u>Length</u>	<u>Width</u>
1	0.0	0.0	4.6	4.4
2	0.0	0.0	4.2	4.5
3	0.0	0.0	4.3	4.4
4	0.0	0.0	4.1	4.3
5	<u>0.0</u>	<u>0.0</u>	4.3	4.5
<b>Avg.</b>	<b>0.0</b>	<b>0.0</b>		


The sample submitted, in its original state, **meets** the minimum requirements of the above standard. The char length may not exceed 6.0 inches for any individual specimen and the average afterflame time may not exceed 4.0 seconds in the length or width directions.

Sincerely,

Brian S. Dement

BSD/mr





**DIVERSIFIED**  
**TESTING LABORATORIES, INC.**  
WORLDWIDE SERVICE

“We Test Per Your Request”

336 WEST FRONT STREET  
P.O. BOX 4004  
BURLINGTON, NORTH CAROLINA 27215  
PHONE (336) 227-7710 • FAX (336) 227-1175  
www.diversifiedtestinglabs.com

December 13, 2022

Mr. Alex Kouzmanoff  
AZTEC TENTS  
2665 Columbia Street  
Torrance, CA 90503

Reference: Laboratory Test Report  
Lab Identification No. 52907  
Invoice No. 84298

Dear Mr. Kouzmanoff:

One (1) fabric sample, identified as **LAM TEX**, was received and tested in accordance with the California Administrative Code Title 19--Public Safety, Section 1237.1 Flame Resistance, Small Scale Test. **The sample was tested after 72 hours of leaching.** The results are as follows:

**Test Results**

Specimen Number	After Flame (sec)		Char Length (in)	
	<u>Length</u>	<u>Width</u>	<u>Length</u>	<u>Width</u>
1	0.0	0.0	4.4	5.0
2	0.0	0.0	3.6	4.5
3	4.0	6.0	5.1	4.8
4	0.0	0.0	4.0	4.6
5	<u>0.0</u>	<u>0.0</u>	4.9	4.2
<b>Avg.</b>	<b>1.0</b>	<b>1.2</b>		


The sample submitted, when tested after 72 hours of leaching, **meets** minimum requirements of the above standard. The char length may not exceed 6.0 inches for any individual specimen and the average afterflame time may not exceed 4.0 seconds in the length or width directions.

Sincerely,

Brian S. Dement

BSD/mr





**DIVERSIFIED**  
**TESTING LABORATORIES, INC.**  
 WORLDWIDE SERVICE

“We Test Per Your Request”

336 WEST FRONT STREET  
 P.O. BOX 4004  
 BURLINGTON, NORTH CAROLINA 27215  
 PHONE (336) 227-7710 • FAX (336) 227-1175  
 www.diversifiedtestinglabs.com

December 13, 2022

Mr. Alex Kouzmanoff  
 AZTEC TENTS  
 2665 Columbia Street  
 Torrance, CA 90503

Reference: Laboratory Test Report  
 Lab Identification No. 52907  
 Invoice No. 84298

Dear Mr. Kouzmanoff:

One (1) fabric sample, identified as **LAM TEX**, was received and tested in accordance with the California Administrative Code Title 19--Public Safety, Section 1237.1 Flame Resistance, Small Scale Test. **The sample was tested after 100 hours of accelerated weathering.** The results are as follows:

**Test Results**

<u>Specimen Number</u>	<u>After Flame (sec)</u>		<u>Char Length (in)</u>	
	<u>Length</u>	<u>Width</u>	<u>Length</u>	<u>Width</u>
1	0.0	3.0	3.8	4.2
2	0.0	0.0	3.7	3.7
3	0.0	0.0	4.1	4.3
4	0.0	0.0	4.0	3.5
5	<u>4.0</u>	<u>0.0</u>	4.2	4.0
<b>Avg.</b>	<b>1.0</b>	<b>0.6</b>		

The sample submitted, when tested after 100 hours accelerated weathering, **meets** the minimum requirements of the above standard. The char length may not exceed 6.0 inches for any individual specimen and the average afterflame time may not exceed 4.0 seconds in the length or width directions.

Sincerely,

Brian S. Dement

BSD/mr

